

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
24 February 2005 (24.02.2005)

PCT

(10) International Publication Number  
**WO 2005/016577 A3**

(51) International Patent Classification<sup>7</sup>: **C22F 1/043**,  
C21D 6/04

[US/US]; 1657 Prestwick Lane, Carmel, IN 46032 (US).  
**LAYMON, Steve** [US/US]; 5820 Foolish Pleasure Lane,  
Indianapolis, IN 46237 (US).

(21) International Application Number:  
PCT/US2004/026480

(22) International Filing Date: 16 August 2004 (16.08.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/495,079 14 August 2003 (14.08.2003) US  
60/497,601 25 August 2003 (25.08.2003) US  
60/577,055 4 June 2004 (04.06.2004) US

(71) Applicant (for all designated States except US): **U.S.  
TURBO, LLC** [US/US]; 6228 La Pas Trail, Indianapolis,  
IN 46268 (US).

(72) Inventors; and


(75) Inventors/Applicants (for US only): **CAMPBELL, Tim**

(74) Agents: **DANILUCK, John, V.** et al.; Woodard, Emhardt,  
Moriarty, McNett & Henry LLP, Bank One Center/Tower,  
Suite 3700, 111 Monument Circle, Indianapolis, IN 46204  
(US).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.

[Continued on next page]

(54) Title: PROCESSING FOR CAST COMPONENTS



(57) Abstract: Methods and apparatus for cast metallic components with improved fatigue characteristics. Some embodiments include cryogenic processing of the cast material, such as aluminum C355,354, or A354, and alloys such as Inconel 713C, IN713LC, IN-738, IN-100 or GMR235 prior to or after machining of the cast component. Other embodiments include an object cast from an aluminum compound including up to 1 percent scandium, 1 percent lithium, or combinations of the two.

WO 2005/016577 A3



(84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— with international search report

(88) **Date of publication of the international search report:**  
26 May 2005

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*